Aeschynite (Eschynite) group - Y(TiNb)O₆

Hardness: 5 - 6. Cleavage: Perfect. Inert to acids except in powdered form.

A group of minerals with similar properties. Data given for aeschynite-(Y).

Varieties/related species (treat same as aeschynite group): Priorite = aeschynite-(Y).

References

Mindat: https://www.mindat.org/min-40.html

Handbook of Mineralogy: https://www.handbookofmineralogy.org/pdfs/aeschynite-Y.pdf

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.