

Ancylite group - $\text{CeSr}(\text{CO}_3)_2(\text{OH})\cdot\text{H}_2\text{O}$

Hardness = 4 - 4.5. Cleavage: None observed. Rapidly soluble in acids.

Data given for ancylite-(Ce). Other group members expected to be similar.

References

Mindat: <https://www.mindat.org/min-9156.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/ancylite-Ce.pdf>

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.