

Barylite - $\text{Be}_2\text{Ba}(\text{Si}_2\text{O}_7)$

Hardness = 7. Cleavage: Distinct/good. Excellent acid resistance.

References

Mindat: <https://www.mindat.org/min-545.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/Barylite.pdf>

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.