

Bayldonite - $\text{PbCu}_3(\text{AsO}_4)_2(\text{OH})_2$

Hardness = 4.5. Cleavage: None observed. Slightly attacked by HCl. Soluble in HNO_3 . Attacked by all dithionite recipes.

References

Mindat: <https://www.mindat.org/min-581.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/bayldonite.pdf>

Hardinger, S. (2025) Mineral Specimen Cleaning and Development for the Amateur, 339 p.

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.