

Burbankite - $(\text{Na,Ca})_3(\text{Sr,Ba,Ce})_3(\text{CO}_3)_5$

Hardness: 3.5–4. Cleavage: Imperfect/fair. May be sensitive to acetic acid, formic acid, tartaric acid or citric acid.

References

Mindat: <https://www.mindat.org/min-803.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/burbankite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.