

Chinleite-(Y) - $\text{NaY}(\text{SO}_4)_2 \cdot \text{H}_2\text{O}$

Hardness: 2.5–3. Cleavage: Distinct/good. Brittle. Water sensitive/soluble and therefore intolerant of any aqueous treatment.

References

Mindat: <https://www.mindat.org/min-47890.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/chinleite-Y.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.