

Chloromenite - $\text{Cu}_9(\text{SeO}_3)_4\text{O}_2\text{Cl}_6$

Hardness: 1.5–2.5. Cleavage: Perfect. Water sensitive/soluble and therefore intolerant of any aqueous treatment.

References

Mindat: <https://www.mindat.org/min-6869.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/chloromenite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.