

Djurleite - $\text{Cu}_{31}\text{S}_{16}$

Hardness: 2.5 - 3. Cleavage: None observed. Avoid excess or prolonged heating; this mineral is unstable above 90°C.

References

Mindat: <https://www.mindat.org/min-1300.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/djurleite.pdf>

Cook, W. in Arem, J. (1972) What's new in minerals? Mineralogical Record 3 (1), 14–15.