

Fizélyite - $\text{Ag}_5\text{Pb}_{14}\text{Sb}_{21}\text{S}_{48}$

Hardness: 2. Cleavage: Distinct/good. May be photosensitive; when exposed to light may be altered by air, moisture and/or atmospheric pollutants.

References

Mindat: <https://www.mindat.org/min-1554.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/fizelyite.pdf>

Howie, F., Ed. (1992) The Care and Conservation of Geological Material, 138 p. Routledge, London.

King, R. (1985) The care of minerals section 3A: The curation of minerals. Journal of the Russell Society, 1 (3), 94–113. <https://www.mindat.org/jrs/JRS%20Vol%2001-3.pdf>

Pearl, R. (1982) Cleaning and Preserving Minerals, Fifth Revised Edition, 87 p. Earth Science Publishing Company, Colorado Springs.