

Guerinite - $\text{Ca}_6(\text{HAsO}_4)_3(\text{AsO}_4)_2 \cdot 10.5\text{H}_2\text{O}$

Hardness: 1.5. Cleavage: No data. Brittle. May be sensitive to acetic acid, formic acid, tartaric acid or citric acid.

References

Mindat: <https://www.mindat.org/min-1767.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/guerinite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.