

Hsianghualite - $\text{Ca}_3\text{Li}_2(\text{Be}_3\text{Si}_3\text{O}_{12})\text{F}_2$

Hardness: 6.5. Cleavage: None observed. Brittle. Attacked by HCl, H₂SO₄ or oxalic acid.

References

Mindat: <https://www.mindat.org/min-1937.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/hsianghualite.pdf>

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.