

Kochsándorite - $\text{CaAl}_2(\text{CO}_3)_2(\text{OH})_4 \cdot \text{H}_2\text{O}$

Hardness: 2–2.5. Cleavage: No observed. Brittle. Likely sensitive to all acids to some extent.

References

Mindat: <https://www.mindat.org/min-27424.html>

Handbook of Mineralogy: <https://handbookofmineralogy.org/pdfs/kochsándorite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.