

Lammerite - $\text{Cu}_3(\text{AsO}_4)_2$

Hardness: 3.5–4. Cleavage: Distinct/good. May be sensitive to acetic acid, formic acid, tartaric acid, citric acid, alkalis, NH_3 or dithionite.

References

Mindat: <https://www.mindat.org/min-2314.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/lammerite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.