

Luzonite - Cu_3AsS_4

Hardness: 3.5. Cleavage: Distinct/good. Attacked by HNO_3 or HCl . Dull coatings generally cannot be removed without destroying the specimen. Treat like enargite.

References

Mindat: <https://www.mindat.org/min-2461.html>

Handbook of Mineralogy: <http://www.handbookofmineralogy.org/pdfs/luzonite.pdf>

Rohner, T. (2000) Properly clean minerals online cleaning book.

www.strahlen.org/stepbystep/mineralien-reinigung2.pdf. In German.

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.