Morenosite (Nickel Vitriol) - $NiSO_4 \cdot 7H_2O$

Hardness: 2–2.5. Cleavage: Distinct/good. Soluble in water, dilute acids and ethanol and therefore intolerant of any aqueous treatment. Gains or loses water; store in sealed container.

References

Mindat: https://www.mindat.org/min-2782.html

Handbook of Mineralogy: https://www.handbookofmineralogy.org/pdfs/morenosite.pdf

Deeson, A., Ed. (1973) The Collector's Encyclopedia of Rocks & Minerals, 288 p. Clarkson N. Potter, Inc., New York.

Howie, F., Ed. (1992) The Care and Conservation of Geological Material, 138 p. Routledge, London.

King, R. (1982) The cleaning of minerals. Journal of the Russell Society, 1 (1), 42–53. https://www.mindat.org/jrs/JRS%20Vol%2001-1.pdf

King, R. (1985) The care of minerals section 3A: The curation of minerals. Journal of the Russell Society, 1 (3), 94–113. https://www.mindat.org/jrs/JRS%20Vol%2001-3.pdf

Kipfer, A. (1972) The Micromounter, 211 p. Ott Verlag Thun, Switzerland. In German.

Pearl, R. (1982) Cleaning and Preserving Minerals, Fifth Revised Edition, 87 p. Earth Science Publishing Company, Colorado Springs.

Rohner, T. (2000) Properly clean minerals online cleaning book. www.strahlen.org/stepbystep/mineralien-reinigung2.pdf. In German.

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.

Weast, R., Ed. (1982) CRC Handbook of Chemistry and Physics, 63rd Edition, 2380 p., CRC Press, Inc., Cleveland.

Wight, Q. (1993) The Complete Book of Micromounting, 281 p. Mineralogical Record, Tucson, Arizona.