

Nabokoite - $\text{KCu}_7(\text{SO}_4)_5(\text{Te}^{4+}\text{O}_3)\text{OCl}$

Hardness: 2–2.5. Cleavage: Perfect. May be sensitive to acetic acid, formic acid, tartaric acid, citric acid, NH_3 , alkalis or dithionite. Hygroscopic; store in sealed container with desiccant.

References

Mindat: <https://www.mindat.org/min-2823.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/nabokoite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.