

Népouite - $\text{Ni}_3\text{Si}_2\text{O}_5(\text{OH})_4$

Hardness: 2–2.5. Cleavage: Poor/indistinct. Attacked by oxalic acid, concentrated HCl or concentrated H_2SO_4 .

References

Mindat: <https://www.mindat.org/min-2875.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/neltnerite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.