

Pentahydroborite - $\text{CaB}_2\text{O}(\text{OH})_6 \cdot 2\text{H}_2\text{O}$

Hardness: 2.5. Cleavage: None observed. Attacked by HCl or oxalic acid. May be sensitive to H_2SO_4 .

References

Mindat: <https://www.mindat.org/min-3154.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/pentahydroborite.pdf>

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.