

Pyatenkoite-(Y) - $\text{Na}_5\text{YTi}[\text{SiO}_3]_6 \cdot 6\text{H}_2\text{O}$

Hardness: 4–5. Cleavage: Distinct/good. Very sensitive to HCl. Attacked by H_2SO_4 or oxalic acid.

References

Mindat: <https://www.mindat.org/min-7259.html>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland