

Quetzalcoatlite - $\text{Zn}_6\text{Cu}_3(\text{TeO}_6)_2(\text{OH})_6 \cdot \text{Ag}_x\text{Pb}_y\text{Cl}_{x+2y}$

Hardness: 3. Cleavage: Imperfect/fair. Brittle. May be sensitive to acetic acid, formic acid, tartaric acid, citric acid, alkalis, NH_3 or dithionite.

References

Mindat: <https://www.mindat.org/min-3343.html>

Handbook of Mineralogy: <http://www.handbookofmineralogy.org/pdfs/quetzalcoatlite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.