

## Schoenfliesite - $\text{Mg}[\text{Sn}(\text{OH})_6]$

Hardness: 4–4.5. Cleavage: None observed. May be sensitive to acetic acid, formic acid, tartaric acid or citric acid. Sensitive to strong alkalis.

### References

Mindat: <https://www.mindat.org/min-3573.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/schoenfliesite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3<sup>rd</sup> Edition, 190 p. Duthaler, Switzerland.