

Scholzite - $\text{CaZn}_2(\text{PO}_4)_2 \cdot 2\text{H}_2\text{O}$

Hardness: 3 - 3.5. Cleavage: Imperfect/fair. Attacked by H_3PO_4 , HNO_3 , HCl or H_2SO_4 .

References

Mindat: <https://www.mindat.org/min-3576.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/scholzite.pdf>

Rohner, T. (2000) Properly clean minerals online cleaning book.

www.strahlen.org/stepbystep/mineralien-reinigung2.pdf. In German.