

Tanteuxenite-(Y) - $\text{Y}(\text{Ta,Nb,Ti})_2(\text{O,OH})_6$

Hardness: 5.5–6. Cleavage: No data. Brittle. May be hygroscopic; store in sealed container with desiccant.

References

Mindat: <https://www.mindat.org/min-3883.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/tanteuxenite-Y.pdf>

King, R. (1985) The care of minerals section 3A: The curation of minerals. Journal of the Russell Society, 1 (3), 94–113. <https://www.mindat.org/jrs/JRS%20Vol%2001-3.pdf>