

Witherite - BaCO₃

Hardness: 3 - 3.5. Cleavage: Distinct/good. Inert to plain water. Attacked to some extent by all acids. Avoid detergent and soap. Insoluble in methanol, ethanol, isopropanol or acetone.

References

Mindat: <https://www.mindat.org/min-4299.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/witherite.pdf>

DeMouthe, J. (2017) Care and Documentation of Mineral Collections, 94 p. Mineralogical Society of America, Chantilly, Virginia.

Hardinger, S. (2024) Selective removal of carbonates: A preliminary study.

www.mindat.org/a/hardinger005

Hardinger, S. (2025) Mineral Specimen Cleaning and Development for the Amateur, 339 p.

Rohner, T. (2000) Properly clean minerals online cleaning book.

www.strahlen.org/stepbystep/mineralien-reinigung2.pdf. In German.

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.

Weast, R., Ed. (1982) CRC Handbook of Chemistry and Physics, 2380 p., CRC Press, Inc., Cleveland.