

Yanomamite - $\text{InAsO}_4 \cdot 2\text{H}_2\text{O}$

Hardness: 3–4. Cleavage: Poor/indistinct. Brittle. Attacked by HCl or H_2SO_4 .

References

Mindat: <https://www.mindat.org/min-4352.html>

Handbook of Mineralogy: <https://www.handbookofmineralogy.org/pdfs/yanomamite.pdf>

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.