Petrified Wood - ~ SiO_2

Hardness: Varies with composition; probably ~ 7. Cleavage: None observed. Assume physical and chemical properties like agate, chalcedony or jasper. Excellent chemical resistance. Most frequently colorfast but some samples may be bleached by dithionite, oxalic acid or laundry bleach. May be photosensitive.

References

Mindat: https://www.mindat.org/min-8018.html

Brown, J. (2023) Sun exposure...what can sun exposure do? www.mindat.org/mesg-623295.html

Hardinger, S. (2025) Mineral Specimen Cleaning and Development for the Amateur, 339 p. https://www.mincleandev.com/min_clean_dev.pdf

Sinkankas, J. (1970) Prospecting for Gemstones and Minerals, 397 p. Van Nostrand Reinhold Company, New York.

Sinkankas, J. (1972) Gemstone & Mineral Data Book, 346 p. Winchester Press, New York.