Sailaufite - $(Ca,Na,\square)_2Mn^{3+}_3(AsO_4)_2(CO_3)O_2 \cdot 3H_2O$

Hardness: 3.5. Cleavage: Perfect. Brittle. Attacked by HCl or oxalic acid. May be sensitive to all acids to some extent.

References

Mindat: https://www.mindat.org/min-27258.html

Handbook of Mineralogy: https://www.handbookofmineralogy.org/pdfs/Sailaufite.pdf

Duthaler, R. and Weiß, S. (2024) Mineral Cleaning for Collectors, 3rd Edition, 190 p. Duthaler, Switzerland.